

SALT SPRAY (FOG) EXPOSURE TEST PER ASTM B117

Test Procedure

Testing was performed was in accordance with ASTM B117-16, *Standard Practice for Operating Salt Spray (Fog) Apparatus*. Three, 4-inch by 6-inch specimens were placed in a salt spray (fog) chamber and subjected to a total of 300 hours of salt spray exposure with visual examinations made every 100 hours.

The salt spray (fog) chamber was calibrated in accordance with ASTM B117-16.

Test Results

| Specimen No. | Observations |
|--------------|--|
| 1 | No cracking, checking, crazing, erosion, delamination or other deleterious effects were observed after 100, 200 and 300 hours of exposure. |
| 2 | No cracking, checking, crazing, erosion, delamination or other deleterious effects were observed after 100, 200 and 300 hours of exposure. |
| 3 | No cracking, checking, crazing, erosion, delamination or other deleterious effects were observed after 100, 200 and 300 hours of exposure. |