

**WATER RESISTANCE TEST PER ASTM D2247**

**Test Procedure**

Three, 4-inch by 6-inch specimens were placed in an environmental chamber, maintained at 100°F (38°C) and 100% relative humidity, for a period of 120 days. The samples were positioned in the test chamber 15 degrees from the vertical and inspected daily for deleterious effects.

**Test Results**

<b>Specimen No.</b>	<b>Observations</b>
1	After 120 hours of exposure, no deleterious effects such as cracking, crazing, blistering, softening or embrittlement occurred.
2	After 120 hours of exposure, no deleterious effects such as cracking, crazing, blistering, softening or embrittlement occurred.
3	After 120 hours of exposure, no deleterious effects such as cracking, crazing, blistering, softening or embrittlement occurred.